RECEIVED CENTRAL FAX CENTER

OCT 1 0 2006

### AMENDMENTS TO THE CLAIMS

This listing of the claims will replace all prior versions and listings of claims in the application:

#### Listing of Claims:

- (Withdrawn) A process of preparing a polymer composition that includes a branched crystalline diene-modified polypropylene random terpolymer, comprising:

  contacting a metallocene catalyst compound with a polymerization medium that includes at least a propylene monomer, a first diene monomer, and a second diene monomer, in which the first diene monomer and the second diene monomer are different non-conjugated dienes, each having 5 or more carbon atoms; and

  conducting polymerization of the monomers in the presence of the metallocene catalyst
  - conducting polymerization of the monomers in the presence of the metallocene catalyst compound for a time sufficient to provide a branched crystalline diene-modified polypropylene random terpolymer that includes monomeric units derived from each of the monomers, and having from 0.0 wt% to 2.0 wt% ethylene and a heat of fusion of 30 J/g or more.
- 2. (Withdrawn) A process of preparing a polymer composition that includes a branched crystalline diene-modified polypropylene random terpolymer, comprising:

contacting a metallocene catalyst dempound with a polymerization medium that includes at least a propylene monomer, and a an internal non-conjugated diene monomer, and a an on-conjugated diene monomer, and a an on-conjugat

conducting polymerization of the monomers in the presence of the metallocene catalyst compound for a time sufficient to provide a branched crystalline diene-modified polypropylene random terpolymer that includes monomeric units derived from each of the monomers, and having from 0 0 wt% to 2.0 wt% ethylene and a heat of fusion of 30 J/g or more.

- 3. (Withdrawn) The process of claim 1, in which the first diene monomer is an α, internal diene.
- 4. (Withdrawn) The process of claim 1, in which the second diene monomer is an α, ω diene.
- 5. (Withdrawn) The process of claim 1, in which the first diene monomer is an  $\alpha$ , internal non-conjugated diene monomer; and the second diene monomer is an  $\alpha$ ,  $\omega$  non-conjugated diene monomer.


of 19

LABPOLA WAPProsecus lon/EMCC Prosecution/2002/2002B171/LIS/2002B171-2-LIS

- 6. (Withdrawn) The process of claim 1, in which either the first diene monomer or the second diene monomer has an internal double bond comprising a di-substituted vinyl group or a tri-substituted vinyl group.
- 7. (Withdrawn) The process of claim 1, in which either the first diene monomer or the second diene monomer has an internal double bond comprising a di-substituted vinyl group or a tri-substituted vinyl group having one or more methyl group substituents.
- 8. (Withdrawn) The process of claim 1, on which the first diene monomer is an a, internal non-conjugated diene monomer having an internal double bond comprising a trisubstituted vinyl group having two methyl group substituents.
- 9. (Withdrawn) The process of claim 1, in which the second diene monomer is an α, ω diene comprising unsubstituted 4-pentadiene; 1,5-hexadiene; 1,6-heptadiene; 1,7-octadiene; 1,8-nonadiene; or 1,9-decadiene.
- 10. (Withdrawn) The process of claim 1, in which either the first diene monomer or the second diene monomer comprising substituted 1,4-pentadiene; 1,5-hexadiene; 1,6-heptadiene; 1,7-octadiene; 1,8-nonadiene; or 1,9-decadiene.
- 11. (Withdrawn) The process of claim 1, in which the second diene monomer comprises 2-methyl-1,5-hexadiene.
- 12. (Withdrawn) The process of claim 1, in which the first diene monomer comprises 2-methyl-1,5-hexadiene or 7-methyl-1,5-octadiene.
- 13. (Withdrawn) The process of claim, i, in which the amount of the first diene monomer is greater than the amount of the second diene monomer.
- 14. (Withdrawn) The process of claims, in which the first diene monomer is an α, internal non-conjugated diene monomer; the second diene monomer is an α, ω non-conjugated diene monomer; and the amount of the second diene monomer.
- 15. (Withdrawn) The process of claim 1, in which the polymerization medium includes 50 mol% or more propylene monomers, 10 mol% or less α, internal non-conjugated diene monomers, and 1 mol% or less α, φ non-conjugated diene monomers.
- 16. (Withdrawn) The process of claim 1, in which the metallocene catalyst compound is or includes a substituted or unsubstituted silyl-bridged or ethylene-bridged bis-indenyl metallocene.

I:DPCLAWProsecution\2MCC Prosecution\2002\2002\3002\3002\3171\US\2002\B171-2-US\2002\

- 17. (Withdrawn) The process of claimes, in which the metallocene compound comprises a bridged metallocene compound having at least two indenyl rings or derivatives of indenyl rings, each ring being substituted at the 2 position.
- 18. (Withdrawn) The process of claim 1, in which the metallocene compound comprises a bridged metallocene compound having at least two indenyl rings or derivatives of indenyl rings, each ring being substituted at the 2 and 4 positions.
- 19. (Withdrawn) The process of claim 1, in which the metallocene compound comprises supported dimethylsilylbis(2-methyl-4-phenyl-1-indenyl)zirconium dimethyl.
- 20. (Withdrawn) The process of claim 1, in which the metallocene includes a dimethylanilinium tetrakis (perfluorophyl) boron activator.
- 21. (Withdrawn currently amended) The process of claim 1, in which the supported metallocene includes a methylaluminoxane metally luminoxane activator.
- 22. (Withdrawn currently amended) The process of claim 1, in which the metallocene compound is represented by the formula:



M1 is selected from the group consisting of titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum and tungsten;

R1 and R2 are identical or different, and are one of a hydrogen atom, a  $C_1$ - $C_{10}$  alkyl group, a  $C_1$ - $C_{10}$  alkoxy group a  $C_6$ - $C_{10}$  aryl group, a  $C_6$ - $C_{10}$  aryloxy group, a  $C_2$ - $C_{10}$  alkenyl group, a  $C_2$ - $C_{40}$  alkenyl group, a  $C_7$ - $C_{40}$  arylalkyl group, a  $C_7$ - $C_{40}$  alkylaryl group, a  $C_8$ - $C_{40}$  arylalkenyl group, an  $C_8$ - $C_{40}$  arylalkenyl group, an  $C_8$ - $C_{40}$  arylalkenyl group, an  $C_8$ - $C_{40}$  arylalkyl group, a  $C_7$ - $C_{40}$  alkylaryl group, a  $C_8$ - $C_{40}$  arylalkenyl group, an  $C_8$ - $C_{40}$  arylalkenyl group, and  $C_7$ - $C_{40}$  arylalkyl group, a  $C_7$ - $C_{40}$  alkylaryl group, a  $C_8$ - $C_{40}$  arylalkenyl group, a  $C_7$ - $C_{40}$  arylalkenyl group, a  $C_7$ - $C_{40}$  alkylaryl group, a  $C_7$ - $C_{40}$  arylalkenyl group, a  $C_7$ - $C_{40}$  alkylaryl group, a  $C_7$ - $C_{40}$  alk

Each  $R^3$  is identical or different from the other  $R^3$  and is each a hydrogen atom, a halogen atom, a  $C_1$ - $C_{10}$  alkyl group which may be halogenated, a  $C_2$ - $C_{10}$  alkeryl group, a  $C_7$ - $C_{40}$ -arylalkyl group, a  $C_7$ - $C_{40}$  alkylaryl

group, a  $C_8$ - $C_{40}$  arylalkenyl group, a  $NR'_2$ , -SR', -OR',  $-OSiR'_3$  or  $-PR'_2$  radical, wherein R' is one of a halogen atom, a  $C_1$ - $C_1$ 0 alkyl group, or a  $C_6$ - $C_{10}$  aryl group;

R<sup>4</sup> to R<sup>7</sup> are identical or different and are hydrogen, or are as defined for R<sup>3</sup> or two or more adjacent radicals R<sup>5</sup> to R<sup>7</sup> together with the atoms connecting them form one or more rings;

 $-B(R^{14})$ -,  $-Al(R^{14})$ -, -Ge-, -Sn-, -S-, -SO-, -SO-, -SO-,  $-N(R^{14})$ -, -CO-,  $-P(R^{14})$ -, or  $-P(O)(R^{14})$ -;

wherein: R<sup>14</sup>, R<sup>15</sup> and R<sup>16</sup> are identical or different and are a hydrogen atom, a halogen atom, a C<sub>1</sub>-C<sub>20</sub> branched or linear alkyl group, a C<sub>1</sub>-C<sub>20</sub> fluoroalkyl or silaalkyl group, a C<sub>6</sub>-C<sub>30</sub> aryl group, a C<sub>6</sub>-C<sub>30</sub> fluoroaryl group, a C<sub>1</sub>-C<sub>20</sub> alkoxy group, a C<sub>2</sub>-C<sub>20</sub> alkenyl group, a C<sub>7</sub>-C<sub>40</sub> arylalkyl group, a C<sub>8</sub>-C<sub>40</sub> arylalkenyl group, a C<sub>7</sub>-C<sub>40</sub> alkylaryl group, or R<sup>14</sup> and R<sup>15</sup>, together with the atoms binding them, form a cyclic ring;

or, R<sup>13</sup> is represented by the formula:


wherein: R<sup>17</sup> to R<sup>24</sup> are as defined for R<sup>1</sup> and R<sup>2</sup>, or two or more adjacent radicals R<sup>17</sup> to R<sup>24</sup>, including R<sup>20</sup> and R<sup>21</sup>, together with the atoms connecting them form one or more rings;

M<sup>2</sup> is one or more carbons, silicon, germanium or tin; and

R<sup>8</sup>, R<sup>9</sup>, R<sup>10</sup>, R<sup>11</sup> and R<sup>12</sup> are identical or different and have the meanings stated for R<sup>4</sup> to R<sup>7</sup>.

23. (Withdrawn - currently amended) The process of claim 1, in which the metallocene compound is represented by the formula:

bf 19



wherein: M is a metal of Group 4, 5, or 6 of the Periodic Table, for example titanium, zirconium, hafnium, vanadium, niobium, tantalum, chromium, molybdenum and tungsten, preferably, zirconium, hafnium and titanium, most preferably zirconium and hafnium;

 $R^1$  and  $R^2$  are identical or different, and are one of a hydrogen atom, a  $C_1$ - $C_{10}$  alkyl group, a  $C_1$ - $C_{10}$  alkoxy group, a  $C_6$ - $C_{10}$  anyl group, a  $C_6$ - $C_{10}$  arylaxy group, a  $C_7$ - $C_{40}$  arylalkyl group, a  $C_7$ - $C_{40}$  arylalkyl group, a  $C_7$ - $C_{40}$  arylalkenyl group, or a halogen atom, or a corrugated diene which is optionally substituted with one or more hydrocarbyl, trithydrocarbyl)silyl groups or hydrocarbyl, trithydrocarbyl)silyl groups or hydrocarbyl, trithydrocarbyl)silylhydrocarbyl groups, said diene having up to 30 atoms not counting hydrogen;

R<sup>3</sup> and R<sup>4</sup> are defined the same as are R<sup>1</sup> and R<sup>2</sup>;

aniun/2002/2002B171/US/2002B171-2-US

R<sup>5</sup> and R<sup>6</sup> are identical or different, and are one of a hydrogen atom, a halogen atom, a C<sub>1</sub>-C<sub>10</sub> alkyl group, which may be halogenated, a C<sub>6</sub>-C<sub>10</sub> aryl group, which may be halogenated, a C<sub>2</sub>-C<sub>10</sub> alkeny group, a C<sub>7</sub>-C<sub>40</sub> arylalkyl group, a C<sub>7</sub>-C<sub>40</sub> arylalkyl group, a C<sub>7</sub>-C<sub>40</sub> alkylaryl group, a C<sub>8</sub>-C<sub>40</sub> arylalkenyl group, a [[-NR<sub>2</sub><sup>15</sup>]] -NR'<sub>2</sub>, [[-SR<sup>15</sup>]] -SR', [[-OR<sup>15</sup>]] -OR',

[[-OSiR<sub>3</sub>15]] -OSiR'<sub>3</sub> or [[-PR<sub>2</sub>15]] -PR'<sub>2</sub> radical, wherein: [[R<sup>15</sup>]] R' is one of a halogen atom, a  $C_1$ - $C_{10}$  alkyl group or a  $C_6$ - $C_{10}$  ary group;

 $-B(R^{14})$ -,  $-Al(R^{14})$ -, -Ge-, -Sn-, -O-, -S-, -SO-,  $-SO_2$ -,  $-N(R^{14})$ -, -CO-,  $-P(R^{14})$ -, or  $-P(O)(R^{14})$ -;

wherein:  $R^{14}$ ,  $R^{15}$  and  $R^{16}$  are identical or different and are a hydrogen atom, a halogen atom, a  $C_1$ - $C_{20}$  branched or linear alkyl group, a  $C_1$ - $C_{20}$  fluoroalkyl or silaalkyl group, a  $C_6$ - $C_{30}$  aryl group, a  $C_6$ - $C_{30}$  fluoroalkyl group, a  $C_1$ - $C_{20}$  alkoxy group, a  $C_2$ - $C_{20}$  alkenyl group, a  $C_7$ - $C_{40}$  arylalkyl group, a  $C_8$ - $C_{40}$  arylalkenyl group, a  $C_7$ - $C_{40}$  alkylaryl group, or  $R^{14}$  and  $R^{15}$ , together with the atoms binding them, form a cyclic ring;

M2 is carbon, silicon, germanium or tin;

R<sup>8</sup> and R<sup>9</sup> are R<sup>8</sup> and R<sup>9</sup>, are identical or different, and have the meanings stated for R<sup>5</sup> and R<sup>6</sup>;

R<sup>10</sup>, R<sup>11</sup>, R<sup>12</sup> and R<sup>13</sup> are identical or different and have the meanings stated for R<sup>5</sup> and R<sup>6</sup>; wherein at least one of R<sup>13</sup> and R<sup>10</sup> are identical or different, and are one of a hydrogen atom, a halogen atom, a C<sub>1</sub>-C<sub>10</sub> alkyl group, which may be halogenated, a C<sub>6</sub>-C<sub>10</sub> aryl group, which may be halogenated, a C<sub>7</sub>-C<sub>10</sub> alkenyl group, a C<sub>7</sub>-C<sub>40</sub> arylalkyl group, a C<sub>7</sub>-C<sub>40</sub> alkylaryl group, a C<sub>8</sub>-C<sub>40</sub> arylalkenyl group, a [[-NR<sub>2</sub><sup>15</sup>]] -NR''<sub>2</sub>, [[-SR<sup>15</sup>]] -SR'', [[-OR<sup>15</sup>]] -OR'', [OSiR<sub>3</sub><sup>15</sup>]] -OSiR''<sub>3</sub> or [[-PR<sub>2</sub><sup>15</sup>]] -PR''<sub>2</sub> radical, wherein: [[R<sup>15</sup>]] R'' is one of a halogen atom, a C<sub>1</sub>-C<sub>10</sub> alkyl group, or a C<sub>6</sub>-C<sub>10</sub> aryl group; and

<u>2</u>.

m and n are identical or different and are zero[[,]] or 1 er 2, m plus n is zero, 1 or

- 24. (Withdrawn) The process of claim 1, in which the polymerization medium is substantially gel-free following formation of the polypropylene terpolymer.
- 25. (Withdrawn) The process of claim , further comprising crosslinking the polypropylene terpolymer.
- 26. (Withdrawn) The process of claim 1, in which polymerization medium has less than 90 volume percent diluent.
- 27. (Withdrawn) The process of claim, in which polymerization medium has less then 50 volume percent diluent.
- 28. (Withdrawn) The process of claim, in which polymerization medium has less then 30 volume percent diluent.
- 29. (Withdrawn) The process of claim 1, in which the final crystalline polypropylene terpolymer is isotactic or syndiotactic.
- 30. (Withdrawn) The process of claim 1, in which the metallocene catalyst compound is combined with the monomers in the absence of hydrogen or in the presence of hydrogen in an amount of up to 1.0 mole% hydrogen in the reactor.
- 31. (Withdrawn) The process of claim 1, in which the heat of fusion of the crystalline polypropylene is 50 J/g or more.
- 32. (Withdrawn currently amended) the process of claim 1, in which the heat of fusion of the branched crystalline polypropy tene is 70 J/g or more. Add 75 j/g more
- 33. (Withdrawn) The process of claim 1, in which the heat of fusion of the branched crystalline polypropylene is 100 J/g or more.
- 34. (Withdrawn) The process of claim 1, in which the branched crystalline polypropylene has a Branching Index of 0.98 or less.
- 35. (Withdrawn) The process of claim 1, in which the branched crystalline polypropylene has a Branching Index of 0.95 or less.

2 of 19

IABPOLAW Wrosporution/EMOC Provesution/2002/2002B171/US/2002B171-2-US/20

- 36. (Withdrawn) The process of claim 1, in which the branched crystalline polypropylene has a Branching Index of 0.90 or less
- 37. (Withdrawn) The process of claim 1, in which the branched crystalline polypropylene has a Branching Index of 0.80 or less.
- 38. (Currently amended) A polymer composition that includes a branched crystalline dienemodified polypropylene random tempolymer having propylene units; first diene units; second diene units; from 0.0 wt% to 2.0 wt% ethylene units; and a heat of fusion of 30 J/g or more, wherein the first dene units are derived from 2-methyl-1.5-hexadiene monomer or α, internal nonconjugated diene monomers and the second diene units are derived from different α, ω non-conjugated diene monomers, each having 5 or more carbon atoms.
- 39. (Original) The polymer composition of claim 38, in which the random polypropylene terpolymer comprises at least 30% and no more than 95% propylene units; at least 5% and no more than 65% first diene units; at least 0.001% and no more than 2.00% second diene units; and from 0.0 mol% to 3.0 mol% ethylene units.
- 40. (Currently amended) The polymer composition of claim 38, in which the first diene units are derived from α, internal non conjugated diene monomers branched crystalline polypropylene has a Branching Index of 0.95 or less.
- 41. (Currently amended) The polymer composition of claim 38, in which the second diene units are derived from α, ω near conjugated diene monomers branched crystalline polypropylene has a Branching Index of 0.90 or less.
- 42. (Currently amended) The polymer composition of claim 38, in which the first diene monomer is an α, internal non conjugated diene monomer that is units are present in the polypropylene terpolymer in an anount of from 0.0005 mol% to 10 mol%.
- 43. (Currently amended) The polymer composition of claim 38, in which the first diene menomer is an α, internal non-conjugated diene monomer that is units are present in the polypropylene terpolymer in an aniquent of from 0.005 mol% to 1 mol%.
- 44. (Currently amended) The polymer composition of claim 38, in which the first diene monomer is an α, internal-non-conjugated-diene monomer selected from the group consisting of 2-methyl 1,5 hexadigne and units are derived from 7-methyl-1, 6-octadiene.
- 45. (Original) The polymer composition of claim 38, in which the branched final crystalline polypropylene has a crystallization temperature (Tc) of 50°C or more.


13 bf 19

IABPOLA WAProscoulion/SMCC Prosecusion/2007/2002B171/US\2002B171-2-US 2006OCTH-Respo

- 46. (Original) The polymer composition of claim 3B, in which the branched crystalline polypropylene has a crystallization emperature (Tc) of 75°C or more.
- 47. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a crystallization remperature (Tc) of 100°C or more.
- 48. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a crystallization temperature (Tc) of 110°C or more.
- 49. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a crystallization temperature (Tc) of from 50°C to 115°C.
- 50. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melting point [Im] of 75°C or more.
- 51. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melting point film) of 100°C or more.
- 52. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melting point (Im) of 125°C or more.
- 53. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melting point (1m) of 150°C or more.
- 54. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melting point [1m] of 160 °C pr more.
- 55. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melting point (7m) of from 75°C to 160°C.
- 56. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melt flow rate of 0.01 or more.
- 57. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melt flow rate of 0.1 or more.
- 58. (Original) The polymer composition of claim 38, in which the branched crystalline polypropylene has a melt flow rate of 0.5 or more.

4 bf 19

EVERCYLAWYProsecution/EMCC Prosecution/2002/2002B171VLIS/2002B17



- (Original) The polymer composition of claim 38, in which the branched crystalline 61.

# This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

### **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

BLACK BORDERS

IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

FADED TEXT OR DRAWING

BLURRED OR ILLEGIBLE TEXT OR DRAWING

SKEWED/SLANTED IMAGES

COLOR OR BLACK AND WHITE PHOTOGRAPHS

GPAY SCALE DOCUMENTS

LINES OR MARKS ON ORIGINAL DOCUMENT

REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

## IMAGES ARE BEST AVAILABLE COPY.

OTHER:

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.